



Thurmalox® 884 Series Temperature Indicating Coating

Dampney Company's Thurmalox 884 TIC line of temperature indicating coatings allows for a range of temperatures and colors which help to identify hot spots on refractory lined equipment and process vessel overheating. Thurmalox 884 also has uses in the heat treating and OEM industries where an indicator is required as part of a heating or curing process.

- Very sharp, easily seen irreversible color change
- One and two step color change options
- Suitable for shop or field application
- Acceptable for use on ferrous and non-ferrous metals
- Can be recoated with itself after repairs
- Applied over suitable inorganic zinc rich primers, silicone primers or existing coated surfaces
- Applied by brush, roller, conventional or airless spray methods
- Contains no heavy metals

About Us

Dampney Company manufactures a wide range of heat resistant coatings for the refining, chemical processing, power generation, steel processing, mining and OEM industries. Typical applications include the protection of insulated and uninsulated metals exposed to extreme temperatures and corrosion.

Dampney®
Apexior®
Dymacryl®
Elastoid®
Epodur®
Protexior®
Thurmalox®

DAMPNEY COMPANY, INC.

85 Paris Street
Everett, MA 02149 USA

Contact Us

Phone: 617-389-2805
Email: sales@Dampney.com
Web: www.Dampney.com

Product Code	Thurmalox 884-050	Thurmalox 884-080	Thurmalox 884-082	Thurmalox 884-083	Thurmalox 884-085	Thurmalox 884-090
Color	Red	Green	Green	Green	Green	Blue
Continuous Temperature Resistance (no color change)	≤250°F (121°C)	≤450°F (232°C)	≤300°F (149°C)	≤350°F (177°C)	≤550°F (288°C)	≤500°F (260°C)
Indication Temperature (color change)	Red to Pink ≥300°F(149°C)	Green to White ≥520°F(271°C)	Green to Blue ≥356°F(180°C) Blue to White ≥590°F(310°C)	Green to Brown ≥425°F(218°C) Brown to Red ≥580°F(304°C)	Green to White ≥650°F(343°C)	Blue to White ≥590°F(310°C)
Volume Solids	34%	31%	35%	36%	31%	39%
Dry Film Thickness	1.0-2.0 mils (25-50 µm)	1.0-2.0 mils (25-50 µm)	1.0-2.0 mils (25-50 µm)	1.0-2.0 mils (25-50 µm)	1.0-2.0 mils (25-50 µm)	1.0-2.0 mils (25-50 µm)
Theoretical Coverage at 2.0 mils (50 µm)	272 ft ² /gal (6.74 m ² /l)	248 ft ² /gal (6.13 m ² /l)	281 ft ² /gal (6.95 m ² /l)	289 ft ² /gal (7.15 m ² /l)	248 ft ² /gal (6.13 m ² /l)	313 ft ² /gal (7.75 m ² /l)
Components	One	One	One	One	One	One
VOC Lb/Gal (G/L)	4.85 (582)	4.92 (590)	4.63 (555)	4.59 (551)	4.92 (590)	4.42 (530)

1. The condensed data published above is for reference only; please consult full product data sheets for detailed information.
2. Color change is dependent on variables such as time, temperature and thickness of metal surface. Color change or drift is possible based on these variables.
3. Thurmalox 884 Series Temperature Indicating Coating may require painting every 18-24 months depending on operating conditions.
4. See Thurmalox 260C TIC for additional indicating products.